

■ Polyurethane

Property	Representative Value [※]
Specific Gravity	1.13
Tensile Strength [MPa]	29
300% Modulus [Mpa]	9.8
Tensile Elongation [%]	500
Tear strength [MPa]	6.9
Compression permanent set [%]	37
Ball drop resilience [%]	41
Hardness (JIS-A)	90±5
Coefficient of Linear Expansion	1.6×10^{-4}
Cold resistance [°C]	-65~-50
Oil resistance	resist
Chemical resistance	resist(except strong acid and strong base)

※ Test method is based on JIS K6250